

Epradur® PVC-C

This material is a post-chlorinated PVC and has a wide range of applications. It is highly resistant to acids and alkalis. Also the painting and printing is no problem. The material is cadmium-free and has a high stiffness and pressure resistance. The impact resistance is limited, especially at low temperatures.

General properties	Test method	Value	Unit
ISO code:	ISO 1183		
Density:	ISO 1183-1	1,52	g/cm3
Water absorption in Air (23°C / 50% RH)	ISO 62	0,2	%
Water absorption in Air (23°C / 100% RH)	ISO 62	0,5	%
Resistance to hot water	n/a	+	
Weather resistance	n/a	-	
Mechanical properties			
Elongation at break:	ISO 527	15	%
Ball indentation hardness	ISO 2039	150	MPa
Tensile modules of elasticity	ISO 527	2500	MPa
Charpy impact strength - notched	ISO 179	8	kJ/m2
Charpy impact strength - unnotched	ISO 179	No Break	kJ/m2
Compressive stress at 1%	n/a	n/a	MPa
Coefficient of friction	ASTM D 1894	0,4-0,6	
Thermal properties			
Melting temperature	n/a	110	°C
Max. allowable service temp (short period)	n/a	100	°C
Max. allowable service temp (long period)	n/a	95	°C
Min. service temperature	n/a	-40	°C
Coefficient of linear expansion	n/a	70	x10 -6 m/(m*K)
Flammability	UL94	V0	
Electrical properties			
Dielectric dissipation (at 1MHz)	ISO 60250	3	Ω
Electric strength	ISO 60243	40	kV/mm
Volume resistivity	ISO 60093	>10^13	Ω.cm

Date of issue: 4 May 2018

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or in-complete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.