

Erlan® 70

An elastomeric synthetic polyester-based polyurethane. The material is extremely durable and resistant to cut and tear. Available from stock in 70, 80 and 90 Shore A. Very well finished casting. By the elastomeric properties polyurethanes have an excellent damping function (depending on the hardness).

Properties	Test method	Value	Unit
ISO code:	ISO 1183	PUR	
Density:	ISO 1183-1	1,24	g/cm3
Max. allowable service temp (long period)	n/a	60	°C
Min. service temperature	n/a	-10	°C
Hardness (+/- 5°)	ISO 868	72	° Shore A
Tensile strength	DIN 53504	46	Mpa
Elongation at break	DIN 53504	550	%
Tear propagation resistance	DIN 53507	30	N/mm
Abrasion resilience	DIN 53516	30	mm3
Compression set, 24h, 70°C	ISO 815	20	%

Date of issue: 4 May 2018

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or in-complete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.